
jaquar.com





COP-CHR-041PM	
2-way Bib Cock with Wall Flange	
14.66 LPM @ 3 bar	
By using flow regulators (Product should be ordered with suffix as G-2.5 LPM, GA-6.0 LPM, GB-8.0 LPM, GD-3.8 LPM & GE-1.3 LPM @ 3.0 Bar pressure) one can regulate the flow rate.	
0.5 Bar - 5 Bar	
Brass Ingots as per IS:1264-1997	
Cu (58.0-63.0), Sn (0.0-1.0), Pb (0.5-2.5), Ni (0.0-1.0), Al (0.2-0.8), Mn (0.0-0.5), Total	
Impurity (0.0-2.0), Zn (Remainder)	
Brass Rod as per IS:319-1989	
Cu (56.0-59.0), Pb (2.0-3.5), Fe (0.0-0.35), Total Impurity (0.0-0.7), Zn (Remainder)	
Brass Sheets as per IS:410-1977	
Cu (61.5-64.5), Pb (0.0-0.3), Fe (0.0-0.075), Total Impurity (0.0-0.6), Zn (Remainder)	
ABS - Specific Gravity (g/cm2) - (1.06-1.10), Melt Mass Flow Rate (g/10 min.) - (20-26),	
Rockwell Hardness - (95-115), DTUL @ 66 psi (0.45 MPa) (0C) - (78-102)	
ife Cycle EN 200: 200,000 cycles (Standard)	
- 5.0 LAC Cycles as per EN 200*	
16 bar (Pass)	
25 bar (Pass)	
Plating: Nickel-10.0 micron Chromium-0.3 micron	
Salt Spray (500 hrs + Validated)	
Adhesion (Pass)	
WRAS, ACS Approved (M18X1)	
CHROME (CHR)	
* As per in-house testing done on automatic life cycle testing machine made by Giussani, Italy	
DISCLAIMER: Our every effort has been made to ensure factual accuracy, the information presented subject to changes due	
to requirements in different sites, markets and/ or countries. 10% variation in flow rate may be possible. Jaquar reserves the	
right to make the necessary amendments at any time without prior notice.	