## jaquar.com





Description Flow Rate Recommended Water Pressure	ORP-CHR-10053PM Angular Stop Cock with Wall Flange 40.24 LPM @ 3 bar 0.5 Bar - 5 Bar
Flow Rate Recommended Water Pressure	40.24 LPM @ 3 bar 0.5 Bar - 5 Bar
Recommended Water Pressure	0.5 Bar - 5 Bar
	Brass Ingots as per IS:1264-1997
	Cu (58.0-63.0), Sn (0.0-1.0), Pb (0.5-2.5), Ni (0.0-1.0), Al (0.2-0.8), Mn (0.0-0.5), Total
	Impurity (0.0-2.0), Zn (Remainder)
Brass Specification in	Brass Rod as per IS:319-1989
Percentage	Cu (56.0-59.0), Pb (2.0-3.5), Fe (0.0-0.35), Total Impurity (0.0-0.7), Zn (Remainder)
	Cu (56.0-59.0), Pb (2.0-5.5), Pe (0.0-0.55), Total impunity (0.0-0.7), 2n (Remainder)
	Brass Sheets as per IS:410-1977
	Cu (61.5-64.5), Pb (0.0-0.3), Fe (0.0-0.075), Total Impurity (0.0-0.6), Zn (Remainder)
Cartridge Specification	Fittings : Components have WRAS Approved for food grade conformity with Brass Housing
	and Spindle
	Life Cycle EN 200: 200,000 cycles (Standard)
	- 5.0 LAC Cycles as per EN 200*
Water Tightness	16 bar (Pass)
Pressure Resistance	25 bar (Pass)
Finish	Plating: Nickel-10.0 micron Chromium-0.3 micron
	Salt Spray (500 hrs + Validated)
	Adhesion (Pass)
Available Colour Finishing	Antique Bronze (ABR), Antique Copper (ACR), Black Chrome (BCH), Black Matt (BLM), Gold
	Dust (GDS), Auric Gold (GLD), Graphite (GRF), Stainless Steel Finish (SSF) & White Matt
	(WHM)
* As per in-house testing done on automatic life cycle testing machine made by Giussani, Italy	
DISCLAIMER: Our every effort has been made to ensure factual accuracy, the information presented subject to changes due	
to requirements in different sites, markets and/ or countries. 10% variation in flow rate may be possible. Jaquar reserves the	
right to make the necessary amendments at any time without prior notice.	